

Thinset Recommendation Chart

 	Comparable		Comparable (Pro Favorite)		Comparable		
	Superior Platinum White/50lbs 90sf at 1/4 x 1/4 in.	Ardex X4 Gray and White/40lbs 85-90sf at 1/4 x 1/4 in.	Superior Bond White/50lbs 90sf at 1/4 x 1/4 in.	Ardex X5 Gray and White/40lbs 85-90sf at 1/4 x 1/4 in.	Superior Bond LFT White/50lbs 100sf at 1/4 x 1/4 in.	Ardex X77 Gray and White/40lbs 110sf at 1/4 x 1/4 in.	Superior Maxlite White/30lbs 80sf at 1/4 x 1/4 in.
Ceramic, Cement Encaustic, Quarry	✓	✓	✓	✓	✓	✓	✓
Porcelain	✓	✓	✓	✓	✓	✓	✓
Natural Stone	✓	✓	✓	✓	✓	✓	✓
Glass	—	—	—	—	✓ ₃	✓ ₃	✓ ₃
Large Format Tile Wall Use/Non-Sag	✓	✓	✓	✓	✓	✓	✓
Large Format Tile Floor Use/Non-Slump	✓	✓	✓	✓	✓	✓	✓
Concrete Subfloor, Cement Board, Drywall	✓	✓	✓	✓	✓	✓	✓
Tile Over Tile	✓ ₁	✓ ₁	✓ ₁	✓ ₁	✓ ₁	✓ ₁	✓ ₁
Wet Area <i>Not Submerged</i>	✓	✓	✓	✓	✓	✓	✓
Pool, Steam Shower <i>Submerged</i>	—	—	—	—	✓	✓ ₄	✓
Floor	✓	✓	✓	✓	✓	✓	✓
Wall	✓	✓	✓	✓	✓	✓	✓
Exterior	✓ ₂	✓ ₂	✓ ₂	✓ ₂	✓ ₂	✓ ₂	✓ ₂
Commercial, High Traffic	✓	✓	✓	✓	✓	✓	✓

- Recommended**
- Suitable**
- Not Suitable**

1. Must be sound, solid and well-bonded to underlying, structurally sound substrates. Surface must be prepped with scratch coat or with Superior Primer/Ardex P4 Primer. Questions about this application should be directed to Manufacturer Rep.
2. Not Over Wood
3. Interior Only
4. No Salt Water, Add E90 For Glass On Water Line