

PRO-LASTIC

Pro-Lastic is our highest grade latex-modified thinset when combined with Pro-Lastic Part A Liquid Latex Admixture. Pro-Lastic can be used on almost any surface: sheet rock, tile backer board, exterior glued plywood, concrete, vinyl, over existing tile, masonry, or any questionable surface.

Key Features

- Interior and Exterior use; suitable for residential and commercial construction
- Excellent non-sag properties
- Highly latex-modified two-part system
- Excellent freeze thaw resistance when combined with Pro-Lastic Admixture
- Meets or exceeds ANSI Standards 118.4 & 118.11

Installation

- Packaging:** Part A: 1 Gal, 2 Gal
Part B: 25lb and 50lb bags,
- Colors:** White and Grey
- Mixing Ratio:** 1 Gallon of Pro-Lastic A or water per 25lb
2 Gallons of Pro-Lastic A or water per 50lb
- Coverage:** Approx. 80 sq. ft. per 50lb.
1/4" Sq. Notch Trowel: 75 sq. ft.
3/8" Sq. Notch Trowel; 60 sq. ft.
1/2" Sq. Notch Trowel; 40 sq. ft.

Related Products

- Spiral Mixer 24"
- Bucket 3.5 Gal | 6 Gal
- Margin Trowel

Performance

- Open time:** 20 - 30 minutes
- Working time:** 20 - 30 minutes
- Pot life:** Approx. 3 hours
- Shelf Life:** 15 months. Store in a cool, dry location

Steps to Mix Thinset

- ① Add Pro-Lastic Part A to a bucket; or add 5 - 5.5 quarts of water per 50lb. Liquid Part A comes in 1 and 2 gallon sizes.
- ② Pour powder into the bucket until the admixture/water forms a ring around the powder.
- ③ Use a spiral mixer to mix the thinset to a "peanut butter" consistency. Let it slake for 10-15 minutes, then mix again.
- ④ Use product within Pot Life. Do not re-temper*. If thinset is no longer workable, discard the thinset and mix a new batch.
* Add additional water and remix after initially activating product.

